


TECHNICAL DATA SHEET ACID RESISTANT EPDM RUBBER SHEET

Vulcanised sheets made of EPDM rubber (ethylene-propylene-diene rubber) stands out for its exceptionally good capacity for reversible deformation, which occurs under the influence of mechanical forces. The deformation occurs while maintaining the continuity structure of the material. This feature remains unchanged even when exposed to temperatures as high as +110°C. Celsius. EPDM rubber remains elastic even at a temperature of -40°C.

THE RUBBER IS RESISTANT TO:

- Hot water and steam up to +150 °C.
- Glycol-based brake oils up to 150 °C
- Organic and inorganic acids
- Alkalis: potassium and sodium bases and cleaning agents
- Hydraulic fluids based on phosphate esters
- Silicone based oils and greases
- Polar solvents such as ketones, esters and alcohols
- Skydrol 500 and 7000
- Effects of ozone and UV radiation
- Ageing under atmospheric conditions
- Does not discolour or stain other materials



Hardness (H)	^o ShA	65 ±5
Tensile strength (TS_b) min	MPa	4
Relative elongation after rupture (E_b) min	%	200

Relative permanent deformation after compression at constant strain after 24h, at temp.

70 °C	%	≤ 50		
100 ⁰ C	%	≤ 60%		
Resistance to heat ageing in air at 100 °C after 72 h				
Strength change ΔTS_b	%	±30		
Elongation change ΔE_b	%	-50		
Shore hardness change ΔH	^o ShA	±10		
Density (p) max	Mg/m³	1,40		

PRO-HURT ul. Wandy 18 40-322 Katowice biuro@pro-hurt.pl tel./fax.32247-26-87 www.pro-hurt.pl The sheets are manufactured in the following dimensions:

Thickness (mm)	Roll width (mm)	Roll length (m)	
1	1200	10	
2	1200	10	
3	1200	10	
4	1200	10	
5	1200	10	
6	1200	10	
8	1200	10	
10	1200	10	
12	1200	10	
8	sheet size 1000x1000mm		
10	sheet size 1000x1000mm		
12	sheet size 1000x1000mm		
15	sheet size 1000x1000mm		
20	sheet size 1000x1000mm		
25	sheet size 1000x1000mm		
30	sheet size 1000x1000mm		
40	sheet size 1000x1000mm		
50	sheet size 1000x1000mm		

* This data sheet is confidential. Transmitting, copying and disclosing it to third parties requires the written consent of PRO-HURT. The present data sheet is directed at the addressee(s) referred to above and is the property of the addressee. Disclosure of the card is prohibited. If you are not the intended addressee, you must delete this document immediately and notify the sender by phone or email.

> PRO-HURT ul. Wandy 18 40-322 Katowice

biuro@pro-hurt.pl tel./fax.32247-26-87 www.pro-hurt.pl