

Kaowool 1400 paper



DESCRIPTION

Kaowool 1400 Paper is manufactured from high purity refractory fibres and designed for high temperature insulation. Advanced production techniques ensure uniform fibre distribution and close control of thickness and density.

Kaowool 1400 Paper is produced from Alumina-Silicate fibres with the minimum addition of carefully selected bonds, which burn out cleanly in service. Kaowool 1400 Paper exhibits excellent strength, flexibility and good handling characteristics. Other beneficial properties include low thermal conductivity, low thermal mass and exceptionally high thermal shock resistance

TYPE

Refractory Ceramic Fibre Paper.

CLASSIFICATION TEMPERATURE

1400°C

The maximum continuous use temperature depends on the application. In case of doubt, refer to your local Morgan Thermal Ceramics distributor for advice.

www.morganadvancedmaterials.com

Europe: +44 (0) 151 334 4030 / marketing.tc@morganplc.com

North America: +1 (0) 706 796 4200 / northamerica.tc@morganplc.com

South America: +54 (11) 4373 4439 / marketing.tc@morganplc.com

Asia: +65 (0) 6595 0000 / asia.mc@morganplc.com

Kaowool 1400 paper

Main Properties

Classification Temperature	°C	1400
Typical Physical Properties		
Colour		White
Density	kg/m ³	210
Melting point (minimum)	°C	1760
Tensile strength	kN/m ²	750
Thickness measurement pressure	kPa	10
High Temperature Performance		
Binder content/loss on ignition	%	6
Shrinkage (24 hours at 1260°C)	%	3
Thermal conductivity (BS 1902 Part 6) at mean temperature of		
400°C	W/m.K	0.089
600°C	W/m.K	0.132
800°C	W/m.K	0.197
1000°C	W/m.K	0.293
1200°C	W/m.K	0.436

Chemical composition		
Al ₂ O ₃	%	47
SiO ₂	%	52
Other oxides	%	1

Acoustic absorption coefficient (BS 3638) - 2.0mm thickness:	
Frequency/ HZ	Coefficient
100	0.05
500	0.02
1000	0.07
2000	0.26
4000	0.50

Kaowool 1400 paper

Indicative heat loss table:

Hot face	Insulation Thickness/mm				
	0.5mm	1.0mm	2.0mm	4.0mm	8.0mm
538°C	400	335	268	202	145
649°C	471	395	316	239	172
760°C	-	456	364	276	200
871°C	-	516	413	315	229
982°C	-	-	462	353	258
1093°C	-	-	510	393	290
1204°C	-	-	-	433	321
1260°C	-	-	-	453	337

Combustibility

Alumino-silicate refractory fibres are non-combustible when tested in accordance with BS 476, Part 4.

Availability and Packaging

Thicknesses available: 0.5mm, 1mm, 2mm, 3mm, 4mm, 5mm & 6mm Standard roll widths: 500mm, 610mm, 1000mm & 1220mm.

The values given herein are typical values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Thermal Ceramics office to obtain current information.

www.morganadvancedmaterials.com

Europe: +44 (0) 151 334 4030 / marketing.tc@morganplc.com

North America: +1 (0) 706 796 4200 / northamerica.tc@morganplc.com

South America: +54 (11) 4373 4439 / marketing.tc@morganplc.com

Asia: +65 (0) 6595 0000 / asia.mc@morganplc.com